

## THE INTERNATIONAL GROUP, INC.

USA: 1007 East Spring Street · Titusville, PA 16354 · Toll Free: 1-800-852-6537 · Telephone: (814) 827-4900 · Fax: (814) 827-2363 Canada: 50 Salome Drive · Toronto, Ontario M1S 2A8 · Toll Free: 1-800-561-3509 · Telephone: (416) 293-4151 · Fax: (416) 293-5858 Website: www.igiwax.com

# **IGI<sup>®</sup> 2243A**

IGI<sup>®</sup> 2243A is a specialty formulation of petroleum derived paraffin waxes.

### PHYSICAL PROPERTIES

	ASTM	SPECIFICATIONS		
TEST METHODS	METHOD	Minimum	Maximum	TYPICAL
Melt Point °F (°C)	D 87	126 (52.2)	131 (55)	129 (53.9)
Kinematic Viscosity, cSt @ 212°F (100°C)	D 445	3.0	4.2	3.63
Oil Content, Wt%	D 721		2.5	0.4
Saybolt Color	D 6045	+26		+30
Odor	D 1833		1	0
Needle Penetration, dmm @ 77°F (25°C)	D 1321	14	30	22

Note: Physical properties for which ONLY a typical value is listed are included as additional information but may not be printed on the COA.

### FDA STATUS:

This product meets the FDA requirements set forth in 21 CFR 178.3710 for use in contact with food. For additional FDA compliance information, please contact your IGI Sales Representative.

4/11/17

#### WARRANTY DISCLAIMER STATEMENT

WARRANTY DISCLAIMER STATEMENT beyond the control of THE INTERNATIONAL GROUP, INC. the product's specified characteristics cannot be guaranteed and are offered solely for the buyer's evaluation and verification. SELLER (AND THE INTERNATIONAL GROUP, INC. the product's specified characteristics cannot be guaranteed and are offered solely for the buyer's evaluation and verification. SELLER (AND THE INTERNATIONAL GROUP, INC. AND ANY OF ITS OFFICERS, EMPLOYEES, PARENTS, SUBSIDIARIES, OR AFFILIATES) MAKES NO WARRANTY OF FANY KIND WHATSOEVER WITH RESPECT TO THE DATA OR INFORMATION PROVIDED, OR THE PRODUCTS OR GOODS, INCLIDING ANY (a) WARRANTY OF MERCHANT ABILITY; (b) WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE; (c) WARRANTY OF TITLE; OR (d) WARRANTY AGAINST INFRINGEMENT OF INTELLECTUAL PROPERTY RIGHTS OF A THIRD PARTY; WHETHER ARISING BY LAW, COURSE OF DEALING, COURSE OF PERFORMANCE, USAGE OF TRADE OR OTHERWISE, NOR ANY OTHER WARRANTY, REPRESENTATION, OR CONDITIONS, EXPRESS OR IMPLIED, IN CONNECTION WITH THE SALE OF THE PRODUCTS DESCRIBED IN THIS BULLETIN. Furthermore, INTERNATIONAL GROUP, INC. assumes no liability or obligation in connection with use of this information. Accordingly, the buyer and each user assumes all risks and liability in connection with their use of such products. Nothing contained herein is to be construed as permission, recommendation or inducement by THE INTERNATIONAL GROUP, INC. or its officers, employees, parents, subsidiaries or affiliates, to use any product or process so as to infringe or conflict with any patent. Further, it is the user's obligation to utilize this material in full compliance with health, safety and environmental regulations. THE INTERNATIONAL GROUP, INC. recommends that the Material Safety Data Sheet for this product be consulted prior to handling.